



# Variolink® Veneer / Syntac®

## Light-cure Resin Cement


Placement of ceramic restorations where adequate light penetration is available



Restoration




Preparation



Pre-treatment of restorations according to manufacturer's instructions

### Monobond Plus




### Enamel Total Etch




### Syntac Primer





### Syntac Adhesive



Enamel and dentin



### Variolink Veneer




### Liquid Strip




# Variolink® Veneer / Syntac®

## Lichthärtendes Befestigungscomposite

Für die rein lichthärtende Befestigung von transluzenten Vollkeramiken




Provisorium entfernen




Einprobe Restauration

### Restauration



Absolute Trockenlegung

### Präparation



Vorbehandlung der Restauration  
nach Herstellerangaben



AIR!



H2O



AIR!

### Schmelz Total Etch



15–30 sec



H2O



AIR!

### Syntac Primer



15 sec



H2O



AIR!

### Syntac Adhesive




10 sec




H2O







AIR!




Heliobond  
Schmelz und Dentin



### Variolink Veneer



5 sec





5 sec



30 sec

### Liquid Strip



30 sec



30 sec

CE 0123